

ClayTec HFA N+F D20

Item No. 09.221

**Thickness= 20 mm, L= 1.350 mm, W= 600 mm,
butt groove and tongue**


- **Low-emission wood fibreboard (HFA)**
- **Lightweight**
- **Joints possible in the field**
- **Small format is ideal for the Do-It-Yourself builders**



View wall



View roof slope



Wood fibreboard (HFA) for cladding of wood and metal post structures of inner walls, facing shells, ceiling and roof surfaces. ClayTec HFA N+F are light and breathable. The small format and the tongue-and-groove ensure best workability, even joints are possible in the field. It is very reasonably priced, making low-emission drywall affordable for everyone! As supplement to this product sheet the **ClayTec guidelines for „Low-emission drywall systems“**.



GERMANY

© claytec GmbH & Co. KG
Nettetal Straße 113-117
D-41751 Viersen-Boisheim
+49 (0)2153 918-0
service@claytec.com
claytec.com

2026/9
Changes and errors excepted.
Current version available at
claytec.com

ClayTec HFA N+F D20

Item No. 09.221

Thickness= 20 mm, L= 1.350 mm, W= 600 mm,
butt groove and tongue

Scope of application Wood fibreboard (HFA) for cladding of wood and metal post structures in the interiors. For inner walls and facing shells DIN 4103-1, installation area 1 or 2 for ceiling and roof surfaces. On surfaces of water exposure class W0-I as per DIN 18534-1, e.g. in bathrooms (except for shower area) and household kitchens. For full-surface cladding of solid wood components, boarding, and wood-based panels. With reinforcing layer substrate for YOSIMA clay design plaster or ClayTec clay topcoat fine O6 with ClayFix clay paint as well as other ClayTec clay plaster.

Composition Wood fibers

Characteristic values Compressive strength ≥ 150 kPa. Bulk density approx. 250 kg/m³, Thermal conductivity value 0.05 W/mK, μ 5. Heat storage: Cp 21 kJ/kgK, 10.5 kJ/m²K. Fire behaviour according to DIN EN 13501-1: E

Component values For stability as per DIN 4103-1, sound insulation of walls and facing shells as well as building material class and fire resistance class for walls and ceilings, please refer to **ClayTec guidelines for „Low-emission drywall systems“**.

Dimensions and weights Thickness= 20 mm, L= 1.350 mm, W= 600 mm (Effective measure 0.78 m²/board). Mass of approx. 4 kg/board = approx. 5 kg/m².

Delivery form 112 boards/individual pallets.

Storage In storage flat on pallets, dry. Storage is unlimited. Protect against moisture during transport and storage on construction site. On the construction site, store flat and even on dry pallets or wood. Protect edges against damages.

Humidity Moisture stress due to wet installed plaster or screed is not allowed. In general, the relative air humidity should not exceed 70 % during storage and after installation.

Material requirement When determining material requirements take into account reserves of approx. 10 % for waste, etc. Allow approx. 15 % extra fasteners.

Substructure Wood posts: Solid wood (soft wood) as per DIN EN 14081-1 or laminated timber (BSH) in accordance with DIN EN 14080. Strength class min. C24 according to DIN EN 338. Sorting class S10 according to DIN 4074 Moisture content max. 18 %.

Metal posts: Sheet steel profile according to DIN 18182-1 / DIN EN 14195.

Grid walls: axles dimension distance 500 mm.

Grid ceilings and roof pitches: axles dimension distance 350 mm.

The edges are designed with special tongue-and-groove which allows for joints even in the field. The blanks must then be attached on two substructure components.

The wall-mounted substructure sections are supported with ClayTec drywall tape and mounted according to rules of engineering. For studding make sure that the boards are mounted on the substructure offset by 90°. We strongly advise against mounting directly on the load bearing components (e.g. Rafters, ceiling beams).

The moisture content of cladding substrates made of solid wood components, boarding, and wood-based panels must be checked due to the risk of drying deformation and subsequent damage to claddings and coatings.

Processing The long and deep embedding tongue-and-groove connection is used for component stability. Their geometry requires special care during transport and installation. Imperfections in joint areas can be tolerated to a certain extent (< 10 cm, < 20 % Total joint length).

The boards can be cut, among others, with Jigsaw or hand-held circular saw, see also the clip on www.youtube.com/watch?v=5FFMZ6PX7dY

The side to be plastered is the light, sanded side printed with the product name. For panels produced before 10.12.2022 (recognisable by the date stamp on the panel), the non-printed side must be plastered. The bottom row of the boards must be mounted with some spacing to ("Air") the floor. They must be mounted in landscape format and as tightly as possible.

Screws: Mounting on wood with ClayTec clay building board screws 5 x 50 mm or FN drywall screws with coarse thread. On the metal C-Profile with FN drywall screws with fine double-thread, on UA profile with TB drywall screws and countersunk washer. Screwing distance ≤ 200 mm, i.e. 4 mounting points are required for each board/substructure crossing. Lower the screws a bit (board flush).

Brackets: Mounting on wood with brackets 45 mm, e.g. Haubold Art. No. 574941 KG 745 Cnk resined 12 μ m (ETA). Bracket spacing ≤ 65 mm.

Lay the boards with tongue pointing upwards. Cross jointing and continuation of wall opening limits through horizontal or vertical joints are not allowed. Mount with joints offset by a post spacing of min. 300 mm. Use joints to connect to other building parts such as solid walls and ceilings.

Further treatment The room temperature should not exceed +10 °C for joint and coating works. In general, keep the moisture penetration through the plaster to as low as possible. Use ClayTec clay joint-filler for closing the wall-mounted board joint.

Carefully dust off the boards before mortar application.

Thin-layer coating: Finely and deeply fill gaps at board joint at ≥ 1 mm wide with ClayTec clay adhesive and reinforcing mortar or clay topcoat fine O6, close screw recesses and imperfections, allow to dry. The surfaces are coated 3 mm thick with clay adhesive and reinforcing mortar. It can also be injected with a plaster machine, rest times are not required for this application. Glass or flax fabric is worked into the still wet surface. After drying professionally apply YOSIMA clay design plaster. For the YOSIMA clay surfacer or the CLAFIX clay coating system the fabric of the reinforcing layer is covered wet-on-wet.

Thick-layer coating: Close gap ≥ 1 mm wide as before. The surfaces are pretreated with RED primer. Apply clay base plaster straw, clay plaster mineral or SanReMo on wall surfaces in a layer thickness of max. 8 mm and max. 5 mm on ceiling or roof pitch surfaces. Glass or flax fabric is worked into the still wet surface. Allow to dry. Total plaster thickness for the wall max. 15 mm, ceiling or roof pitches max. 10 mm (each at least in two layers).

Wall surface heating: Close gap ≥ 1 mm wide as before. Prepare the surfaces with RED primer or with notched trowel made of clay adhesive and reinforcing mortar. Allow to dry. Pre-spray up to max. 8 mm with clay plaster mortar mentioned above. Polish up after drying up to pipe crow wall heating. Drying of the entire base plaster with heating support. For further information see ClayTec work sheet Clay Plaster.

Familiarity with **ClayTec guidelines for „Low-emission drywall systems“** is mandatory for the handling the products.

Claims for compensation that do not result from factory mixing errors are excluded. Subject to change and errors excepted. As of 2026/9.