

Clay thin-bed mortar

Art. 10.150

- For load-bearing and non-load-bearing walls
- For vertically perforated clay bricks
- For vertically perforated bricks
- For KS and lightweight concrete blocks



ClayTec clay thin-bed mortar is a high-performance masonry mortar for load-bearing clay masonry up to building class 5, brick masonry up to building class 4, and non-load-bearing masonry of any kind. It contains no fired binders such as cement or lime. This reduces the energy required for production while also avoiding the high alkalinity associated with conventional mortars during application.

Thanks to its water solubility, ClayTec clay thin-bed mortar creates reversible bonds and makes solid masonry suitable for circular construction. Bricks, sand-lime blocks, and lightweight concrete blocks can be dismantled, separated by material type, and preserved for reuse. ClayTec also offers coordinated system solutions for circular interior construction.

ClayTec®

GERMANY

© ClayTec GmbH & Co. KG
Nettetalter Straße 113-117
D-41751 Viersen-Boisheim
+49 (0)2153 918-0
service@claytec.com
claytec.com

2026/9

Changes and errors excepted.
Current version available at
claytec.com

Clay thin-bed mortar

Art. 10.150

Application Thin-bed mortar as a dry ready-mix for bonding sufficiently level masonry units and plan blocks for load-bearing clay brick and brick masonry using the thin-bed method, in accordance with the general building approval / general type approval Z-17.6-1306 and general type approval Z-17.11-1327.
Suitable for non-load-bearing interior masonry without fire protection requirements.

Composition Sand up to 1.0 mm, clay, talcum, perlite, plant fibers, and cellulose.

Building material values Grain size group, max. grain size 0/1, < 2 mm, bulk density class 1.6, drying shrinkage 0.4 %, strength class M2.5, compressive strength 3.8 N/mm²;
Characteristic shear bond strength¹⁾ with vertically perforated clay brick 0.04 N/mm²,
Characteristic shear bond strength²⁾ with vertically perforated brick 0.04 N/mm²,
Characteristic shear bond strength³⁾ with molded clay brick 0.23 N/mm²,
Characteristic shear bond strength³⁾ with vertically perforated brick 0.20 N/mm²;
μ-value 5/10, thermal conductivity 0.73 W/m·K, building material class A1.2

Yield One 25 kg bag yields approximately 17 liters of mortar for about 18 m². Masonry bonded in stock joints from 4 or 8 DF-blocks, wall thickness 11.5 cm, or for approximately 12 m² masonry bonded in stock joints from 12 DF-blocks, wall thickness 17.5 cm.

Storage Proper dry storage indefinitely possible.

Mortar preparation The 25 kg dry mass is gradually mixed with 8.5-9.0 liters of clean water using a suitable mixer. Processing consistency should be pasty for application using a thin-bed mortar sled, mortar roll, or application roller. After 30 minutes of maturation, mix thoroughly again. The mortar is now ready for application.

Processing The stones of the masonry must be dry, dust-free, clean, frost-free, and sufficiently absorbent. Do not process the mortar at temperatures < 5 °C. At high temperatures, the mortar may set unusually quickly. Thin-bed mortar is applied without voids to the bearing surfaces of the plan blocks in approximately 2 mm thickness, the following layer is immediately set into the freshly plastic mortar layer.

Hardening The hardening time depends on the absorbency of the masonry stones and the climatic conditions; during the drying time, the masonry must not be exposed to frost. The masonry must be protected from moisture during and after drying.

Claims for compensation that do not result from factory mixing errors are excluded. Subject to change and errors excepted.
As of 2026/9.

¹⁾ according to AbZ / ABg Z-17.6-1306

²⁾ according to ABg Z-17.11-1327

³⁾ according to testing